



BASIC USES & GENERAL INFORMATION

ROOF MATE BASECOAT was especially developed for use in embedding reinforcement fabric at detail areas and/or over the entire roof. It is also used for achieving film build prior to topcoating with **ROOF MATE**, **ROOF MATE QS**, **ROOF MATE HT** or **ROOFSHIELD** Finish Coat. It is formulated to achieve superior adhesion

over metal, conventional built-up, modified bitumen, single-ply, concrete, board-stock and sprayed-in-place polyurethane foam, and composite shingle roof substrates. **ROOF MATE BASECOAT** forms a waterproof elastomeric seal, uniformly covering the textured profile of these substrates.

PRODUCT DESCRIPTION

ROOF MATE BASECOAT is a high solids, waterbased acrylic elastomer coating utilizing the latest advances in acrylic technology. It combines acrylic emulsion polymers with reinforcing laminar pigments, powerful biocides and non-migrating fire retardants for superior physical properties, adhesion, durability, weatherproofing, mildew resistance and fire retardancy. The fire retardant chemicals are permanently locked into the cured coating and will not leach out upon extended weathering. **ROOF MATE BASECOAT** is a "breathing" coating, allowing moisture vapor to pass through the film while remaining impervious to mass water penetration.

WARRANTY

ROOF MATE is backed by 5, 10 and 15 year, non-prorated warranty programs. All warranty programs are extendable to last for the life of the structure.

PACKAGING & SHELF LIFE

5 gallon (19 liter) bucket
55 gallon (208 liter) drum

Shelf life 24 months if unopened containers stored between 40°F and 70°F.

PERFORMANCE PROPERTIES

ROOF MATE BASE COAT	
Solids by Weight	67% (±2) [ASTM D2369]
Solids by Volume	51% (±2) [ASTM D5201]
Weight per Gallon	11.8 lbs. (±.2) (1.41 kg/l) [ASTM D1475]
Tensile Strength	182 psi (±20) (1.83 MPa) [ASTM D2370/D6083]
Elongation	135% (±20) [ASTM D2370/D6083]
Hardness	60 to 70 Shore A [ASTM D2240]
Permeance	2.7 US perms at 22 dry mils (155ng/(Pa.s.m²)@560 microns) [ASTM E96]
Fire Resistance	UL 790 Class "B" classified system over spray-applied polyurethane foam on combustible decks, when used with Roof Mate Topcoats.

Dry Time for Water Resistance:*	3 hours at 75°F (24°C), 50% R.H. *Required time will increase at higher humidity and/or lower temperatures
Low Temperature Flexibility	Passes 180° flex over ½" (1.2 cm) mandrel @ -5°F (-21°C) [Federal Test Method No. 141a-6221]
Temperature Limits for Normal Service Conditions	0°F to 200°F (-18°C to 93°C)
Standard Colors	Medium gray color, which provides for a high visual contrast with the application of the subsequent ROOF MATE Finish Coat.

APPLICATION INSTRUCTIONS

Mixing: Use a power mixer capable of uniformly mixing the entire container prior to use. **ROOF MATE BASECOAT** is easily pumped and sprayed at material temperatures of 60°F (16°C) or greater. Reducing the mixture is not recommended, as it affects the coatings ability to achieve a heavy film build with excellent vertical hold and hide.

Surface Preparation: All surfaces must be clean and dry, and free of any dirt, dust, oil, surface chemicals or other contaminants that may interfere with optimum adhesion. All loose gravel, if present, shall be removed by power sweeping and/or vacuuming. Remaining gravel shall be power spud to achieve the smoothest surface possible. Any unsound areas in the roof, i.e. blisters, delamination, deterioration, moisture saturation, severe corrosion, sharp projections, ridges, etc. shall be repaired or replaced. New asphalt shall be exposed to ambient conditions for 45 to 60 days before coating.

Deteriorated or badly corroded metal shall be replaced. Rusted areas shall be mechanically abraded to remove all loose rust and then primed with UNITED'S Acrylex 400 or Primer 302 LV. New metal roofs exhibiting any type of surface film shall be washed with a vinegar or muriatic acid

solution, or equivalent, to totally remove this film. Low areas that hold excessive ponding water must be brought into conformance by installing additional drains or adding additional slope to existing drains.

Surfaces that are contaminated with oil, grease, embedded dirt, loose paint or coating, etc. shall be cleaned using United Cleaning Concentrate (UCC). High-pressure power washing may be necessary to remove tightly adhering contaminants. Power-rinse thoroughly with clean water to remove all traces of the UCC cleaner. If roof does not require chemical cleaning, thoroughly sweep, vacuum or blow down roof to remove any dirt, dust or other loose contaminants. Refer to separate Roof Mate Master Guide Specifications for complete surface preparation procedures on the specific substrate being coated.

Application: Reinforce all "moving" cracks, seams, splits, control joints, vertical/horizontal interfaces, roof termination points, openings, transition areas, around the base of all vents pipes and other protrusions, as well as around HVAC units and other roof mounted equipment with **ROOF MATE** Mesh, a polyester reinforcement fabric, embedded into **ROOF MATE BASECOAT**.

ROOF MATE Base Coat

Technical Data Sheet



Page 2 of 2

APPLICATION INSTRUCTIONS (CONT'D)

Pre-measure the area to be reinforced and cut a strip of 4", 6" or 12" (10, 15 or 20 cm) **ROOF MATE** Mesh (depending upon the detail) to the desired length. Apply **ROOF MATE** BASECOAT liberally over the area to be detailed, at a minimum rate of 1.5 gallons per 100 ft² (.6 l/m²), and embed the mesh so that it is centered over the detail area. Using a brush or roller, work the **ROOF MATE** Mesh into the **ROOF MATE** BASECOAT to eliminate air pockets, wrinkles and gaps. Apply additional **ROOF MATE** BASECOAT as necessary, at a minimum of 1 gallon per 100 ft² (.4 l/m²), to ensure that the **ROOF MATE** Mesh is thoroughly saturated, encapsulated and fully adhered to the substrate. When incorporating **ROOF MATE** Fabric for reinforcement of the entire roof, apply **ROOF MATE** BASECOAT at the rate of 1.5 gallons per 100 ft² (.6 l/m²) to a 4' (1.2 m) wide section of roof where the fabric reinforcement will begin. Embed and encapsulate the end of the reinforcement fabric roll so that it is anchored at that point.

Roll or spray-apply **ROOF MATE** BASECOAT to a section of roof 4 to 10 feet (1.2 to 3 meters) beyond the fabric at the rate of approximately 1.5 gallons per 100 ft² (.6 l/m²). Roll the reinforcement fabric over the wet **ROOF MATE** BASECOAT, allowing the fabric to conform to the surface contours. To ensure complete encapsulation of the fabric, it must be rolled into the **ROOF MATE** BASECOAT while it is still wet. Do not allow the **ROOF MATE** BASECOAT to surface skin prior to rolling out the fabric.

Work the **ROOF MATE** BASECOAT evenly throughout the **ROOF MATE** Fabric so that it is totally saturated, eliminating any air pockets, wrinkles or gaps. Apply an additional coat of **ROOF MATE** BASECOAT over the top of the saturated **ROOF MATE** Fabric at the rate of approximately 1 gallon per 100 ft² (.4 l/m²) so that it is totally encapsulated. Take extra care to ensure that edges of the fabric are well saturated and adhered. Overlap consecutive passes of **ROOF MATE** Fabric a minimum of 2" (5 cm) on each side. Substrate porosity and texture will determine the amount of **ROOF MATE** BASECOAT required to encapsulate the reinforcing fabric. Allow the **ROOF MATE** BASECOAT to dry thoroughly prior to applying **ROOF MATE** Finish Coat to the roof. When using **ROOF MATE** BASECOAT to achieve film build prior to application of the **ROOF MATE** Finish, apply at the rate of 1 to 1½ gallons per 100 ft² (.4 to .6 l/m²) per coat to achieve the desired film thickness.

ROOF MATE BASECOAT may be applied by airless spray equipment or roller. Brush or roller may be used for touch-up and edging work, or for small areas that are not practical for spray application. Airless spray is best suited for field application. **ROOF MATE** BASECOAT can be used to obtain up to ½ of the total dry film thickness requirement specified. However, under no circumstances should the subsequent **ROOF MATE** Finish be less than 12 dry mils in thickness at any location.

LIMITATIONS & PRECAUTIONS

ROOF MATE BASECOAT should generally not be used over cold storage tanks or buildings where a vapor barrier is required. **ROOF MATE** BASECOAT will freeze and become unusable at temperatures below 32°F (0°C), or when there is a possibility of temperatures falling below 32°F (0°C) within a 24-hour period after application. **ROOF MATE** BASECOAT requires complete evaporation of water to cure. Cool temperatures and high humidity retard cure. Do not apply if weather conditions will not permit complete cure before rain, dew, fog or freezing temperatures occur. Do not apply in the late afternoon if heavy moisture condensation may appear during the night. **ROOF MATE** BASECOAT may be applied to a wide range of clean, dry and structurally sound substrates.

Slope for positive drainage is recommended for any roofing application. It is the responsibility of the applicator to ensure that the roof is sound and sloped properly, and that the expansion joints, vents and flashings have been installed as specified or required. Avoid breathing of vapor or spray mist. For exterior applications, approved (MSHA/NIOSH) chemical cartridge respirator must be worn by applicator and personnel in vicinity of application. Check filters frequently to ensure proper protection. If used indoors, provide mechanical exhaust ventilation. During indoor spray operations, air line masks or positive pressure hose masks must be worn. Avoid contact with eyes and contact with skin.

SAFETY & HANDLING

For specific information regarding safe handling of this material, please refer to the Material Safety Data Sheet (MSDS).

CLEAN UP

Thoroughly rinse application equipment with clean water.

Quest Construction Products

1465 Pipefitter Street
N Charleston, SC 29405
855-817-3082
www.quest-cp.com

Our products are guaranteed to meet established quality control standards, information contained in our technical data is based on laboratory and field testing, but is subject to change without prior notice. No guarantee of accuracy are given or implied, nor does Quest Construction Products assume any responsibility for coverage, performance on injuries resulting from storage, handling or use of our products. Liability, if any, is limited to product replacement or, if applicable, to the terms stated within the executed project warranty.