



For more information
Or to buy this product
[Click here](#)

APPLICATION GUIDELINE:

NOVATUFF COATING SYSTEM OVER PLYWOOD OR DENSDECK WITH FULL FABRIC

10 YEAR WARRANTY SYSTEM

GENERAL

The following is a specification only intended for the application of NovaTuff roofing system over plywood or densdeck roof decking. Each project will have special conditions and these should be identified and addressed in addition to this specification. If in doubt, please seek NovaTuff advice before proceeding.

QUALITY ASSURANCE

NovaTuff guarantees that the products specified for this application will perform for the warranty period if installed by a NovaTuff certified applicator in compliance with NovaTuff guidelines and material data instructions.

A pre-installation conference, including at least contractor, applicator, architect/engineer and NovaTuff representative, should be held prior to application, to ensure proper substrate and other conditions.

INSPECTION

Prior to commencement of work, a thorough inspection of the roof surface should be carried out to determine or confirm the following:

The availability of a satisfactory surface for application.

A positive slope to the roof drainage system

and that this system is functioning properly.

The soundness and proper detailing of roof mounted supports, penetrations, flashing, outlets, turn-ups, and all other items that are to be a part of the new, completed roofing system.

The presence of rust or scale, or loose joints or fasteners.

The presence of ponding water and areas at which standing water has previously occurred or is occurring.

The soundness of the existing coating, if the roof has been coated, and the compatibility of the coating and NovaTuff. If in doubt, compatibility should be determined by performing a pull test.

Do not apply NovaTuff roofing product to surfaces that would be considered unsuitable to the manufacturer.

PREPARATION

Protect all adjacent surfaces not designed to receive NovaTuff roofing product.

Clean and prepare all surfaces to receive NovaTuff roofing product by removing all loose

flaking particles, grease and other foreign debris with the use of a stiff bristle push broom and a minimum of 3000 psi power wash.

Make all necessary repairs and secure existing seams before applying NovaTuff roofing product.

For any roof under 5 years old, apply **NovaTuff P-525 PrePrime** over entire roof surface and allow it to sit on roof for 20 minutes. Power wash entire area, maintaining minimum psi mentioned earlier

Surfaces displaying any algae growth must be cleaned with bleach and water solution and thoroughly rinsed before coating.

Do not apply NovaTuff roofing product to surfaces that would be considered unsuitable to the manufacturer.

APPLICATION OF COATING

Detail **NovaTuff RC-155** and fabric components around all penetrations; apply a minimum of six inches up penetration and six inches out onto the roof surface. Apply with brush at the rate of 2 gallons per 100 square feet, lay fabric into wet **NovaTuff RC-155** and saturate top with an additional coat at the rate of 2 gallons per 100 square feet.

Where the roof perimeter forms a 90° angle, install a cant-strip as needed.

Install **NovaTuff RC-155** and twelve inch fabric around perimeter, centering fabric on the cant

strip or seam of edge flashing. All overlaps between fabric sheets must be a minimum of 4 inches. Apply **NovaTuff RC-155** at a rate of 1-1/2 gallons per 100 square feet, lay fabric into wet coating and saturate top with an additional coat at the rate of 1-1/2 gallons per 100 square feet.

Base Coat – Starting at the lowest point, Apply **NovaTuff RC-155** at the rate of 1-1/2 gallons per 100 square feet laying 40 inch wide fabric into wet coating. Brush or sweep fabric into the wet coating to fully adhere it to substrate, then top coat with **NovaTuff RC-155** at the rate of 1-1/2 gallons per 100 square feet. Lap 40 inch fabric a minimum of four inches onto itself and where it intersects any detail work. 40 inch fabric will be installed over the entire roof.

Mid Coat – Apply **NovaTuff RC-100** Roof Coating over fabric at a rate of 1 gallon per 100 square feet (16 wet mils).

Top Coat – Apply **NovaTuff RC-100** Roof Coating at a rate of 1 gallon per 100 square feet (16 wet mils) per coat.

PONDING WATER

For areas of ponding water apply an additional 1 coat of **NovaTuff RC-100** at the rate of 1 gal per 100 square (16 wet mils). Extending coating a minimum of one foot beyond those areas determined in INSPECTION 3.5.

Check NovaTuff for correct thickness in a grid pattern every 400 sq. ft. with wet mil gauge to ensure uniform thickness.

NOVATUFF PRODUCTS USED

NovaTuff RC-100 Roof Coating Part A & B
 NovaTuff RC-155 Tie Coat
 NovaTuff P-525 PrePrime
 NovaTuff Fabric (6", 12", & 40")

Novasol, Inc. reserves the right to continue to improve the product technology. Information contained in this specification could be superseded by changes in performance characteristics. These changes, should they occur, will not be to the detriment of the product.