


R-Tech® EPS Fanfold Recover Board



Overview

R-Tech Fanfold Recover Board is a high-performance rigid insulation consisting of a superior closed-cell, lightweight and resilient expanded polystyrene (EPS) with advanced polymeric laminate facers. R-Tech is available with factory-adhered metallic-reflective facers, white facers or a combination of the two. The EPS core of R-Tech Fanfold Recover Board meets or exceeds the requirements of ASTM C578, Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation. R-Tech Fanfold Recover Board has excellent dimensional stability, compressive strength and water-resistant properties. R-Tech Fanfold Recover Board is an ENERGY STAR®-qualified insulation and can contribute toward LEED® certification credits.

R-Tech Fanfold Recover Board is manufactured by Insulfoam, a division of Carlisle Construction Materials Incorporated with nine manufacturing facilities in North America.

Features and Benefits

- Laborsaving, accordion-style fanfold product allows installers to carry 400 square feet at one time versus 13 sheets of conventional 4' x 8' cover board
- Reduced fastening patterns and lightweight handling reduces labor costs by 50%
- Water-resistant cover board does not break down like alternative cover boards if leaks occur
- Reduces installed costs compared to wood fiber or gypsum by 40% to 60%
- Unique polymeric laminate facers permit PVC to be used without slip sheets

- Metallic facer permits usage under mechanically fastened EPDM in northern locations (Contact WeatherBond Design Services for guidance)
- Nationwide stocking locations
- UL code approval for numerous recover applications
- Approximately 8x higher R-value than ½" gypsum cover boards and 3x higher R-value than ½" wood fiber boards

Product Characteristics

- Panel thickness: ½"
- Panel density: 1 psf
- Bundle size: 4' x 50' (200 ft.²)

Installation

Loose Laid

Install R-Tech Fanfold Recover Board with continuous side joints, and end joints staggered so they are offset by a minimum of 12" from the end joints in adjacent rows. R-Tech Fanfold Recover Board should abut tightly against adjacent boards. Joints greater than ½" should be filled with the same insulation that is being used in the field of the roof. If R-Tech Fanfold Recover Board is being installed over an existing layer of insulation, all joints must be offset a minimum of 6" between layers.


Mechanically Attached

Install R-Tech Recover Board with continuous side joints, and end joints staggered so they are offset by a minimum of 12" from the end joints in adjacent rows. Insulation should abut tightly against adjacent boards. Joints greater than ½" should be filled with the same insulation that is being used in the field of the roof. If R-Tech Fanfold Recover Board is being installed over an existing layer of insulation, all joints must be offset a minimum of 6" between layers. Use an approved mechanical fastener of sufficient length to penetrate into or through the deck by the amount prescribed for the specific fastener. Fasteners should never be closer than 6" from the edges of the insulation board, and should be placed in a pattern to achieve the desired approval. Use appropriate insulation plates with the fasteners. Care must be taken to avoid over-driving or under-driving the fastener and plate assembly.

REVIEW CURRENT WEATHERBOND SPECIFICATIONS AND INSTALLATION GUIDE FOR SPECIFIC APPLICATION REQUIREMENTS.

R-Tech EPS Fanfold Recover Board

WeatherBond-Approved Fastening Pattern



Typical Properties and Characteristics

Physical Property	Test Method	Typical
Nominal Density (pcf)	ASTM C303	1.25
C-Value (Conductance) BTU/(hr • ft ² • °F) (per inch)		
@25°F	ASTM C518	.22
@40°F	or	.24
@75°F	ASTM C177	.26
R-Value (Thermal Resistance) (hr • ft ² • °F)/BTU (per inch)		
@25°F	ASTM C518	4.54
@40°F	or	4.25
@75°F	ASTM C177	3.92
Compressive Strength (psi, 10% deformation)	ASTM D1621	16
Flexural Strength (psi)	ASTM C203	40
Dimensional Stability (maximum %)	ASTM D2126	<2%
Water Vapor Transmission (perms)	ASTM E96	<1.0
Absorption (% vol.)	ASTM C272	<1.0
Capillarity	—	none
Flame Spread	ASTM E84	<20
Smoke Developed	ASTM E84	150 – 300

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.

LEED Information

Post-industrial Recycled Content	Up to to 25%
Manufacturing Locations	Anchorage, AK Kent, WA Dixon, CA Chino, CA Phoenix, AZ Salt Lake City, UT Aurora, CO Mead, NE Lakeland, FL