



**PRODUCT DATA SHEET**

**WINFAB 350N**



**WINFAB 350N** is a needlepunched nonwoven geotextile manufactured using polypropylene fibers that are formed into a dimensionally stable network, which allows the fibers to maintain their relative position.

**WINFAB 350N** resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV English	MARV Metric
Tensile Strength (Grab)	ASTM D-4632	90 x 90 lbs	401 x 401 N
Elongation	ASTM D-4632	50%	50%
CBR Puncture	ASTM D-6241	260 lbs	1157 N
Trapezoidal Tear	ASTM D-4533	40 x 40 lbs	178 x 178 N
UV Resistance (500 hrs)	ASTM D-4355	70%	70%
Apparent Opening Size (AOS)*	ASTM D-4751	50 US Std. Sieve	0.30 mm
Permittivity	ASTM D-4491	2.0 sec <sup>-1</sup>	2.0 sec <sup>-1</sup>
Water Flow Rate	ASTM D-4491	150 gpm/ft <sup>2</sup>	6112 lpm/m <sup>2</sup>

\*Maximum Average Roll Valve

**Notes:**

- Mullen Burst ASTM D-3786 has been removed. It is not recognized by ASTM D-35 on Geosynthetics.
- Puncture ASTM D-4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D-6241

PROPERTY	Typical English	Typical Metric
Roll Dimensions	12.5 x 360 ft 15 x 360 ft	3.81 x 109.8 m 4.6 x 109.8 m
Roll Area	500 yd <sup>2</sup> 600 yd <sup>2</sup>	418 m <sup>2</sup> 502 m <sup>2</sup>

**Disclaimer:** Willacoochee Industrial Fabrics assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. Willacoochee Industrial Fabrics disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.

© 2013 Willacoochee Industrial Fabrics, Inc.

Distributed by: **BEST MATERIALS®**  
 Ph: 800-474-7570, 602-272-8128 Fax: 602-272-8014  
 www.BestMaterials.com Email: Sales@BestMaterials.com

**Willacoochee Industrial Fabrics, Inc.**  
 PO Box 599 • 769 West Main Street • Willacoochee, GA 31650  
 Ph: (912) 534-5757 • Fax: (912) 534-5533

