

PRODUCT DATA

7^{07 19 16} Water
Repellents**ENVIROSEAL[®] 20**

Clear, water-based 20% silane penetrating sealer

Description

Enviroseal[®] 20 is a clear, water-based 20% alkylalkoxysilane penetrating sealer. It protects against moisture and chloride intrusion.

Yield

Concrete:

100 – 175 ft²/gal (2.4 – 4.3 m²/L)

Brick:

100 – 175 ft²/gal (2.4 – 4.3 m²/L)

Stucco:

60 – 100 ft²/gal (1.5 – 2.4 m²/L)

Always apply a test area to determine actual coverage rates. Coverage rates will vary greatly with the porosity of the substrate.

Packaging

5 gallon (19 L) pails

54 gallon (205 L) drums

Color

Milky white liquid; clear when dry

Shelf Life

18 months when properly stored

Storage

Store in unopened containers in a clean, dry area between 35 and 110° F (2 and 43° C).

Features

- Water based, VOC compliant
- USDA compliant (nonfood contact areas)
- Transparent, nonstaining
- Breathable
- One component
- Water repellent

Benefits

- Environmentally friendly
- Use in food manufacturing and service structures
- Does not alter surface appearance
- Allows interior moisture to escape without damaging sealer
- Easy to apply; saves labor
- Protects against damage from moisture intrusion and chloride ion penetration

Where to Use

LOCATION

- Horizontal and vertical
- Exterior or interior
- Above grade

SUBSTRATE

- Concrete
 - Architectural
 - Exposed aggregate
 - Glass-fiber reinforced
 - Precast
 - Cast in place/precast
 - Silica fume
- Hard burnt brick
- Stucco
 - Troweled/smooth
 - Integrally colored
- Brick pavers
- Tile (unglazed)

How to Apply**Surface Preparation**

1. Verify substrate has properly cured. Concrete should obtain 80% of design strength, typically achieved within 14 – 28 days.
2. Clean all surfaces of all sand, surface dust and dirt, oil, grease, chemical films and coatings, and other contaminants prior to application. Use waterblast, sandblast, or shotblast as necessary to achieve the desired surface condition.
3. Air, material, and surface temperatures should be 40° F (4° C) or higher during application. Do not apply sealer when temperatures are expected to fall below 40° F (4° C) within 12 hours.
4. Surfaces to be treated can be slightly damp; however, a dry surface is suggested for maximum penetration of sealer. Do not apply Enviroseal[®] 20 if standing water is visible on the surface to be treated.
5. Crack control, caulking, patching, and expansion joint sealants can be installed before or after application of the sealer. Allow a minimum of 6 – 12 hours curing time for caulking and sealant materials (or until they have skinned over).

Technical Data

Composition

Enviroseal® 20 is a water-based alkylalkoxysilane sealer.

Compliances

- USDA acceptance on nonfood contact areas
- Alberta DOT, Type 1a

Typical Properties

PROPERTY	VALUE
Solids and active ingredients, % by weight	20
Specific gravity, kg/L	0.98
Density, lb/gal	8.16
Penetration, in (mm), average depth, depending upon substrate	0.14 (3.6)

Test Data

PROPERTY	RESULTS	TEST METHODS
Flash point, ° F (° C)	> 200 (> 93)	ASTM D 3278, SETA
VOC content, lb/gal (g/L)	< 2.92 (< 350)	EPA Method 24
Moisture-vapor transmission rate, %	102	OHD-L-35
Water absorption, %, 48 hours	0.53	ASTM C 642
Scaling resistance rating, non-air-entrained concrete, 100 cycles treated concrete	0 – No Scaling	ASTM C 672
Resistance to chloride ion penetration, lb/yd³ (kg/m³) Criteria of 1.5 at 1/2" (13 mm) Criteria of 0.75 at 1" (25 mm)	< 0.27 (< 0.16) 0.00 (0.00)	AASHTO T 259 and T 260
Water weight gain, % reduction	86 – exceeds criteria	NCHRP 244 Series II-cube test
Absorbed chloride, % reduction	92 – exceeds criteria	NCHRP 244 Series II-cube test
Absorbed chloride, % reduction	99 – exceeds criteria	NCHRP 244 Series IV - Southern climate
Water repellent performance, %	85.6	Alberta Transportation and Utilities Procedures - Type 1a
Surface appearance after application	Unchanged	Federal Reflectance Test Method 6121

Test results are averages obtained at a coverage rate of 125 ft²/gal (3.12 m²/3.8 L) under laboratory conditions. Reasonable variations can be expected.

Application

1. Test a small area of the surface (generally a 5 by 5 ft [1.5 by 1.5 m] section) before starting general application of any clear, penetrating sealers to ensure desired results and coverage rates. Allow 5 – 7 days for the product to fully react before evaluating.
2. Stir material thoroughly before and during application.
3. Low-pressure non-atomizing spray application is recommended.
4. On vertical surfaces, apply from the bottom up. Flood surfaces using enough material to get a 8 – 12" (20 – 30 cm) material rundown.
5. For horizontal surfaces, apply to saturation. If necessary, follow by brooming for even distribution.

Drying Time

Typical drying time for Enviroseal® 20 is 4 hours at 70° F (21° C) and 50% relative humidity. Cooler temperatures or higher relative humidity can extend the drying time.

Clean Up

Clean equipment and tools with hot soapy water. Overspray can be cleaned immediately with hot soapy water. Dried residue can be cleaned with a mild citric acid or very hot water, then scrubbed with a plastic sponge.

For Best Performance

- Keep material from freezing.
- Do not dilute Enviroseal® 20.
- Do not apply during inclement weather or when inclement weather is anticipated within 12 hours.
- To prevent damage to nearby shrubbery and landscaping, cover or protect with drop cloth.
- Enviroseal® 20 may leave a temporary slippery surface for up to several hours after application. Therefore, do not reopen traffic-bearing surfaces until the treated surface is dry.
- Variations in the texture and porosity of the substrate will affect the coverage and performance of the product.
- Enviroseal® 20 will not inhibit water penetration through unsound or cracked surfaces, or surfaces with defective flashing, caulking, or structural waterproofing.
- Line striping can be done after application of the sealer.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

Health and Safety

ENVIROSEAL® 20

Caution

Enviroseal® 20 contains alkoxy silane.

Risks

May cause skin, eye or respiratory irritation. Ingestion may cause irritation.

Precautions

KEEP OUT OF THE REACH OF CHILDREN. Avoid contact with skin, eyes, and clothing. Wash thoroughly after handling. Keep container closed when not in use. DO NOT take internally. Use only with adequate ventilation. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable federal, state and local regulations.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION. Refer to Material Safety Data Sheet (MSDS) for further information.

Proposition 65

This product contains material listed by the state of California to cause cancer, birth defects, or other reproductive harm.

VOC Content

Less than 2.92 lbs/gal or 350 g/L, less water and exempt solvents.

**For medical emergencies only,
call ChemTrec (1-800-424-9300).**

**BASF Construction Chemicals, LLC –
Building Systems**

LIMITED WARRANTY NOTICE Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, **BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS,** and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all **CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND.** BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

