



LUCAS Professional Coatings, Sealants & Adhesives

Distributed by: BEST MATERIALS ® LLC
Ph: 800-474-7570, 602-272-8128 Fax: 602-272-8014
www.BestMaterials.com Email: Sales@BestMaterials.com

PRODUCT DATA BULLETIN

#6600

UNIVERSAL™ TERPOLYMER SEALANT

PURPOSE

Lucas #6600 Universal™ Sealant is a high-performance, multipurpose thermoplastic elastomer based sealant. Excellent adhesion to most surfaces including: metal, Kynar®, asphalt, shingles, modified bitumen, EPDM, TPO, Elvaloy/PVC, Hypalon, vinyl, fiber cement, wood, concrete, tile, masonry, glass. #6600 is available in clear, black, white and various colors (see reverse). It is also available in three grades: Standard caulking grade, Self-Leveling Grade (#6600SL) and Winter Grade (#6600W). Use to seal seams, flashings and penetrations on all types of roofs. Ideal for residential roofing applications where appearance is important.



APPLICATION

Surface to be sealed must be clean. Porous surfaces may be primed with Lucas #5015 prior to application of this product. To use, cut tip to size and puncture seal. Maximum recommended joint width and depth is 3/8 inch. Use backer rod for deep joints. Please read the most current Lucas Product Data Bulletin and MSDS for this product prior to use. May be painted. Some paints may require up to one week cure time before application. Keep product warm prior to use. A Winter Grade formula, #6600W, is available for extreme cold weather applications.

CAUTION

Flammable mixture; keep away from heat and open flames. Avoid prolonged contact with skin or fumes. For outdoor use only. If irritation occurs seek medical attention. Do not use near heat or open flame. If swallowed, do not induce vomiting. Keep out of reach of children. Read MSDS prior to use.

California Proposition 65 Warning: This product may contain chemicals known to the State of California to cause cancer, birth defects and/or reproductive harm.

#6600 SPECIFICATION

| | |
|--|---|
| Specification | ASTM C-920, Type S, Grade NS, Class 25, Use NT, except for weight loss. Fed Spec TT-S-00230c, Class A, Type II |
| Recommended rate of application | 3/8" bead max. |
| % Solids by Volume | 69% (Clear 66%) |
| % Solids by Weight | 76% (Clear 70%) |
| Elongation ASTM D-412 | 1000% @ 77°F (25°C) |
| Tensile Strength | 400 psi min |
| Adhesion ASTM C-794 | |
| Shingle | 19 pli |
| TPO | 10 pli |
| PVC/KEE | 13 pli |
| Cement/Mortar | 20 pli |
| Aluminum | 25 pli |
| Steel | 12 pli |
| Kynar® | 19 pli |
| Wood | 22 pli |
| Weight per Gallon | 7.5 lbs |
| VOC | <300 g/l |
| Flash Point (TCC) | +80°F (26.6°C) |
| Container Sizes | 10 oz. tubes |
| Standard Colors: | Clear, White, Black Other Colors see Color Chart |

Listed values are typical for standard grades. Values may vary by color and grade.

TO THE EXTENT ALLOWED BY LOCAL LAW, EXCEPT AS SET FORTH BELOW, SELLER MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE WITH RESPECT TO THE GOODS HEREIN SOLD. THERE ARE NO OTHER WARRANTIES OF ANY KIND EXPRESS OR IMPLIED BEYOND THE TERMS SET FORTH ON THE FACE HEREOF. NO EMPLOYEE OR AGENT OF SELLER IS AUTHORIZED TO ALTER THE TERMS HEREOF.

Seller warrants that this product shall be free of any defect in material or workmanship under normal use for a period of ONE YEAR from the date of purchase. This warranty does not extend to any defect or failure caused by misuse and/or incorrect application. LIMITATION OF LIABILITY: In the event of a defect or failure falling under this warranty, Buyers sole remedy shall be refund of the purchase price or replacement of the defective material, at Seller's option. Under no circumstances shall Seller be liable for any losses or damages caused by this product, whether direct, indirect, special, incidental or consequential damages, whether based on contract, tort (including negligence) or any other legal theory.

NOTE: Some or all of the foregoing may not apply or may be invalid under the laws applicable to Buyer's purchase or claim. Consult local law to determine the applicability of any of the foregoing in the event of any defect or failure of this product.