



LUCAS *Coatings & Mastics for the Roofing Trade*

R. M. Lucas Co. 3211 S. Wood St. Chicago, IL 60608 (773) 523-4300

Distributed by: **Best Materials LLC** Website: www.bestmaterials.com Phone: **800-474-7570, 602.272.8128**

PRODUCT DATA BULLETIN

#758 ALUMINUM ROOF COATING FIBRATED

PURPOSE

#758 Aluminum Roof Coating is designed to provide a reflective surface for roofs, metal buildings, and mobile homes. Aluminum pigmented asphalt coatings can substantially reduce interior building temperature and prolong roof service life. #758 is a heavy-bodied, longer lasting coating that will outlast thinner non-fibered aluminum coatings.



PRODUCT DESCRIPTION

Lucas #758 Aluminum Roof Coating is formulated from specially refined asphalt, aromatic and aliphatic solvents, reinforcing non-asbestos fibers and 2 lbs. per gallon leafing aluminum paste. Formulated to spread easily and evenly by brush or spray.

APPLICATION

Surface to be coated must be dry and free of dirt or corrosion particles. Mechanically mix coating thoroughly and continuously before and during application. Power recommended. Apply evenly with a soft bristle brush or suitable spray equipment rate of not less than one and not more than one and one-half gallons per 100 square For best results, brush coating in one direction with the slope of the roof. Do over fresh roof repairs or coating. Roofing asphalts should be allowed to cure thoroughly to avoid alligating and staining. As this condition is unpredictable, we recommend that the user apply a small amount of #758 to the area of the roof to be order to test its performance. Use #758 as it comes from the container, no thinning necessary with this product. Clean up with Lucas #125 Safe Solve™.

CAUTION

Combustible mixture; keep away from heat and open flames. Avoid prolonged contact with skin or fumes. If irritation occurs seek medical attention. If swallowed, do not induce vomiting. Keep out of reach of children. Read MSDS prior to use.

California Proposition 65 Warning: This product may contain chemicals known to the State of California to cause cancer, birth defects and/or reproductive harm.

#758 SPECIFICATION

Applicable Specification	ASTM D-2824 Type III
Viscosity ASTM D-2196	7000 cps
Recommended rate of application	1 to 1 1/2 gal. per 100 sq. ft
% Asphalt	35 min
% Solids	50 min
% Non-volatile	62 max
Weight per gallon	9.0 lbs.
Flash point (TCC)	+100°F (38.7°C)
Container sizes	5, 55



TO THE EXTENT ALLOWED BY LOCAL LAW, EXCEPT AS SET FORTH BELOW, SELLER MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE WITH RESPECT TO THE GOODS HEREIN SOLD. THERE ARE NO OTHER WARRANTIES OF ANY KIND EXPRESS OR IMPLIED BEYOND THE TERMS SET FORTH ON THE FACE HEREOF. NO EMPLOYEE OR AGENT OF SELLER IS AUTHORIZED TO ALTER THE TERMS HEREOF.

Seller warrants that this product shall be free of any defect in material or workmanship under normal use for a period of ONE YEAR from the date of purchase. This warranty does not extend to any defect or failure caused by misuse and/or incorrect application. LIMITATION OF LIABILITY: In the event of a defect or failure falling under this warranty, Buyers sole remedy shall be refund of the purchase price or replacement of the defective material, at Seller's option. Under no circumstances shall Seller be liable for any losses or damages caused by this product, whether direct, indirect, special, incidental or consequential damages, whether based on contract, tort (including negligence) or any other legal theory.

NOTE: Some or all of the foregoing may not apply or may be invalid under the laws applicable to Buyer's purchase or claim. Consult local law to determine the applicability of any of the foregoing in the event of any defect or failure of this product.