



Distributed by: BEST MATERIALS LLC, Phoenix AZ
Ph: 800-474-7570, 602-272-8128 Fx: 602-272-8014
www.BestMaterials.com Email: Sales@BestMaterials.com

UltraMortar RM

Description:

UltraMortar Roof Mortar is a proprietary mixture of Portland Cement, hydrated lime, ASTM C144 plaster sand.

Uses:

A one-step mortar for placing roof tiles.

Color:

Natural Gray

Packaging:

75 lb. paper sack
90 lb. paper sack

Yield:

Approximately yields as follows:
30 to 50 sq feet
sq ft depend on roofing tile used
and amount of mortar used

Mixing:

To begin, place 2/3 of the required potable water into mechanical mixer. Add one bag of UltraMortar RM. Gradually add remaining water and mix 3-5 more minutes. Stop mixer for 1-2 minutes, then restart to break initial set. Additional water may be added to achieve desired consistency. Keep mixing times consistent from batch to batch.

Limitations:

Use UltraMortar Roof Mortar when surface and ambient conditions are above 38° (13°C) And below 110° (37.5°C) during application and cure time. Strengths may decrease if UltraMortar Roof Mortar is not tooled. High absorptive masonry units may also decrease strengths.

Surface Preparation:

Surfaces must be clean and free of bond-inhibiting materials.

Application:

The time lapse between spreading UltraMortar Roof Mortar and placing roof tiles shall not exceed two minutes. Tooling times should be kept consistent.

Clean Up:

Clean tools and equipment with water immediately after use.

Ultrakote Products
327 South 27th Ave
Phoenix, Arizona 85009
Phone: 602-272-5830 Fax: 602-272-6445