



## SPECIFICATION DATA

### 1. Product Name

Versi-Tite® 16 lb. Industrial Foam Sealant

### 2. Manufacturer

RHH Foam Systems, Inc.  
17100 W. Victor Road | New Berlin, WI 53151

Distributed by: [BEST MATERIALS LLC](http://BESTMATERIALS.LLC)

Ph: 800-474-7570, 602-272-8128

[www.BestMaterials.com](http://www.BestMaterials.com)

Email: [Sales@BestMaterials.com](mailto:Sales@BestMaterials.com)

### 3. Product Description

Versi-Tite® is a one component foam sealant for small gaps and crevices. It is dispensed as a caulking bead, with an approximate 200% expansion rate. It is a moisture cured product using humidity to dry. It is a UL Classified – File #R13919 Caulking and Sealant.

### 4. Technical Data

Versi-Tite® 16 lb. Industrial Foam Sealant has the following physical properties:

<b>DENSITY</b> (ASTM D1622)	1.5 lb/ft <sup>3</sup>
<b>R FACTOR</b> at 1" thickness (ASTM C177)	4.0 to 5.0
<b>AIR BARRIER PROPERTIES</b> (ASTM E283)	
At 6.24 psf (300 Pa)	< 0.01 cfm/ft <sup>2</sup>
At 1.57 psf (75 Pa)	< 0.0025 cfm/ft <sup>2</sup>
<b>CLOSED CELL CONTENT</b> (ASTM D2856)	> 60%
<b>TACK FREE TIME</b>	
At 70°F, 40% RH	Approx. 10 minutes
<b>CUTTABLE</b>	
1" bead at room conditions	1 hour
<b>CURE TIME</b>	12-24 hours
<b>VOC CONTENT</b>	None
<b>ODP</b> (Ozone Depletion Potential)	Contains non ozone-depleting, non-flammable HFC propellant
<b>TEMPERATURE TOLERANCE</b>	
Low Temperature Tolerance	-200°F (-129°C)
High Temperature Tolerance	240°F (115°C)
<b>FLAMESPREAD</b> (ASTM E84)	< 25
<b>SMOKE DEVELOPED</b> (ASTM E84)	< 50
<b>YIELD</b>	
1/4" bead	31,347 linear ft
3/8" bead	13,914 linear ft
1/2" bead	7,827 linear ft
Volume	10.66 cubic ft

\*Published yields are theoretical and vary based on several factors, including ambient conditions and specific application.

\*Always use recommended personal protective equipment. Refer to the Material Safety Data Sheet for additional information on safe use and handling.