



SPECIFICATION DATA

1. Product Name

Versi-Tite® 12 oz. and 24 oz. Foam Sealant

2. Manufacturer

RHH Foam Systems, Inc.
 17100 W. Victor Road | New Berlin, WI 53151
 Phone: 1-800-657-0702 | 262-754-8088
 Fax: 262-754-8089
 Email: sales@rhhfoamsystems.com
 Website: www.rhhfoamsystems.com

3. Product Description

Versi-Tite® is a one component foam sealant for small gaps and crevices. It is dispensed as a caulking bead, with an approximate 200% expansion rate. It is a moisture cured product using humidity to dry. It is a UL Classified – File #R13919 Caulking and Sealant.

4. Technical Data

Versi-Tite® 12 oz. and 24 oz. Foam Sealant have the following physical properties:

DENSITY (ASTM D1622)	1.25 – 1.4 lb/ft ³	
R FACTOR at 1" thickness (ASTM C177)	4.0 to 5.0	
AIR BARRIER PROPERTIES (ASTM E283)		
At 6.24 psf	< 0.01 cfm/ft ²	
At 1.57 psf	< 0.0025 cfm/ft ²	
CLOSED CELL CONTENT (ASTM D2856)	> 70%	
TACK FREE TIME		
At 70°F (21°C), 40% RH	Approx. 5 minutes	
CUTTABLE		
1" bead at room conditions	< 1 hour	
CURE TIME	12-24 hours	
VOC CONTENT	< 20% (low emitting)	
ODP (Ozone Depletion Potential)	Contains non ozone-depleting hydrocarbon propellant	
TEMPERATURE TOLERANCE		
Low Temperature Tolerance	-200°F (-129°C)	
High Temperature Tolerance	240°F (115°C)	
FLAMESPREAD (ASTM E84)	25	
SMOKE DEVELOPED (ASTM E84)	50	
YIELD	12 oz.	24 oz.
1/4" bead	2,201 linear ft	4,403 linear ft
3/8" bead	978 linear ft	1,957 linear ft
1/2" bead	550 linear ft	1,101 linear ft
Volume	.75 cubic ft	1.50 cubic ft

*Published yields are theoretical and vary based on several factors, including ambient conditions and specific application.

*Always use recommended personal protective equipment. Refer to the Material Safety Data Sheet for additional information on safe use and handling.