

FROTH-PAK™ Two-Component Spray Polyurethane Foam Systems



FROTH-PAK™ spray polyurethane foam is a two-component, quick-cure foam that fills cavities, cracks and expansion joints for insulation and air sealing. It is available in disposable kits for smaller jobs and refillable cylinders for applications that require a greater amount.

Note: Consult the instructions and Material Safety Data Sheets carefully before use.

FROTH-PAK™ FOAM SEALANT – KITS

Foam System Description (all products have 15-month shelf life)	R-Value ⁽¹⁾ aged (initial)	Part Numbers	Density, pcf	Theoretical Yield ⁽²⁾ , bd ft	Kit Contents	Shipping Information
FROTH-PAK™ 12 	4.6 (6.3)	308900	1.9	12	1 Iso (A) can 1 Polyol (B) can 1 thumb-controlled spray dispenser with hoses 1 shoulder strap assembly 3 Caulk white spray nozzles - 259211	40 lb (18.1 kg)/12 kits per case 12 cases/pallet
FROTH-PAK™ 120 	5.5 (6.0)	346965	1.75	120	1 Iso (A) cylinder 1 Polyol (B) cylinder 6 Cone white spray nozzles - 259219 4 Fan spray nozzles - 259216 9 ft. gun hose assembly (GHA) 1 petroleum jelly packet	29 lb (13.2 kg)/kit 26 kits/pallet
FROTH-PAK™ 200 	5.5 (6.0)	346963	1.75	200	1 Iso (A) cylinder 1 Polyol (B) cylinder 6 Cone white spray nozzles - 259219 4 Fan spray nozzles - 259216 9 ft. gun hose assembly (GHA) 1 petroleum jelly packet	42 lb (18.6 kg)/kit 26 kits/pallet
FROTH-PAK™ 620 	5.5 (6.0)	"A": 341171	1.75	620	1 Iso (A) cylinder	118 lb/kit (A & B) 12 sets/pallet
		"B": 347036			1 Polyol (B) cylinder	
		GHA: 158398	NA	NA	8 Cone white spray nozzles - 259219 4 Fan spray nozzles - 259216 15 ft. gun hose assembly (GHA) 1 petroleum jelly packet	60 lb (A) Comp 58 lb (B) Comp

FROTH-PAK™ FOAM SEALANT – SPECIALTY KITS

FROTH-PAK™ 115 High Density 	4.5 (5.2)	307466	3.4	90	1 Iso (A) cylinder 1 Polyol (B) cylinder 6 Cone white spray nozzles - 259219 4 Fan spray nozzles - 259216 9 ft. gun hose assembly (GHA) 1 petroleum jelly packet	41 lb (18.6 kg)/kit 26 kits/pallet
FROTH-PAK™ 160 Slow Rise 	4.9 (6.4)	309410	2.9	125	1 Iso (A) cylinder 1 Polyol (B) cylinder 6 Cone white spray nozzles - 259219 4 Fan spray nozzles - 259216 9 ft. gun hose assembly (GHA) 1 petroleum jelly packet	42 lb (19.1 kg)/kit 26 kits/pallet

FROTH-PAK™ FOAM SEALANT – REFILLABLE CYLINDERS ⁽³⁾



Foam System Description (all products have 15-month shelf life)	R-Value ⁽¹⁾ aged (initial)	Part Numbers	Density, pcf	Theoretical Yield ⁽²⁾ , bd ft	Shipping Weight, lb
FROTH-PAK™ 17 	5.5 (6.0)	"A": 341167 "B": 345347	1.75	2,060	Empty cylinder: 60 each Chemical: 150 net Total cylinder weight: 210 each Total system weight: 420
FROTH-PAK™ 60 	5.5 (6.0)	"A": 341165 "B": 345344	1.75	6,860	Empty cylinder: 240 each Chemical: 500 net Total cylinder weight: 740 each Total system weight: 1,480
FROTH-PAK™ 120 	5.5 (6.0)	"A": 341168 "B": 345346	1.75	15,430	Empty cylinder: 390 each Chemical: 1,125 net Total cylinder weight: 1,515 each Total system weight: 3,030
FROTH-PAK™ 350 	5.5 (6.0)	"A": 341166 "B": 345348	1.75	43,890	Empty cylinder: 1,000 each Chemical: 3,200 net Total cylinder weight: 4,200 each Total system weight: 8,400

(1) R-value per inch; ft²•h•°F/Btu; aged LTR measured at 2" thick





(2) The theoretical yield has become an industry standard for identifying certain sizes of two-component kits. Theoretical yield calculations are performed in perfect laboratory conditions, without taking into account the loss of blowing agent or the variations in application methods and types

(3) Gun hose assembly and nozzles available

FROTH-PAK™ FOAM INSULATION – KITS (U.S. ONLY)

Foam System Description (all products have 15-month shelf life)	R-Value ⁽¹⁾ aged (initial)	Part Numbers	Density, pcf	Theoretical Yield ⁽²⁾ , bd ft	Kit Contents	Shipping Information
FROTH-PAK™ 200 	5.6 (6.6)	340316	1.75	200	1 Iso (A) cylinder 1 Polyol (B) cylinder 8 Cone white spray nozzles - 259219 4 Fan white spray nozzles - 259216 9 ft. gun hose assembly (GHA) 1 petroleum jelly packet	42 lb/kit 26 kits/pallet
FROTH-PAK™ 620 	5.6 (6.6)	"A": 340317 "B": 340320	1.75	620	1 Iso (A) cylinder 1 Polyol (B) cylinder	118 lb/kit (A & B) 12 sets/pallet
		GHA:158398			NA	8 Cone white spray nozzles - 259219 4 Fan white spray nozzles - 259216 15 ft. gun hose assembly (GHA) 1 petroleum jelly packet

FROTH-PAK™ FOAM INSULATION – REFILLABLE CYLINDERS⁽³⁾ (U.S. ONLY)

Foam System Description (all products have 15-month shelf life)	R-Value ⁽¹⁾ aged (initial)	Part Numbers	Density, pcf	Theoretical Yield ⁽²⁾ , bd ft	Shipping Weight, lb
FROTH-PAK™ 17 	5.6 (6.6)	"A": 340334 "B": 340321	1.75	2,060	Empty cylinder: 60 each Chemical: 150 net Total cylinder weight: 210 each Total system weight: 420
FROTH-PAK™ 60 	5.6 (6.6)	"A": 340337 "B": 340323	1.75	6,860	Empty cylinder: 240 each Chemical: 500 net Total cylinder weight: 740 each Total system weight: 1,480
FROTH-PAK™ 120 	5.6 (6.6)	"A": 340336 "B": 340322	1.75	15,430	Empty cylinder: 390 each Chemical: 1,125 net Total cylinder weight: 1,515 each Total system weight: 3,030
FROTH-PAK™ 350 	5.6 (6.6)	"A": 340338 "B": 340324	1.75	43,890	Empty cylinder: 1,000 each Chemical: 3,200 net Total cylinder weight: 4,200 each Total system weight: 8,400

(1) R-value per inch; ft²•h•°F/Btu; aged 90 days at 140°F
 (2) The theoretical yield has become an industry standard for identifying certain sizes of two-component kits. Theoretical yield calculations are performed in perfect laboratory conditions, without taking into account the loss of blowing agent or the variations in application methods and types
 (3) Gun hose assembly and nozzles available

FROTH-PAK™ Foam Insulation can be left exposed per NFPA 286 approval testing in roof/wall junctures (maximum 6" high and 2" deep [unlimited length]).

www.dowbuildingsolutions.com

Technical Information
 1-866-583-BLUE (2583) (English)
 1-800-363-6210 (French)

Sales Information
 1-800-232-2436 (English)
 1-800-565-1255 (French)

IN THE U.S.
 THE DOW CHEMICAL COMPANY
 200 Larkin
 Midland, MI 48674

IN CANADA
 DOW CHEMICAL CANADA ULC
 450 – 1st St. SW . Suite 2100
 Calgary, AB T2P 5H1

NOTICE: No freedom from any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries or regions. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY DOW. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

Dow Polyurethane Foam Insulation and Sealants

CAUTION: When cured, these products are combustible and will burn if exposed to open flame or sparks from high-energy sources. Do not expose to temperatures above 240°F (116°C). For more information, consult MSDS, call Dow at 1-866-583-BLUE (2583) or contact your local building inspector. In an emergency, call 1-989-636-4400 in the U.S. or 1-519-339-3711 in Canada.

FROTH-PAK™ spray polyurethane foam contains isocyanate, hydrofluorocarbon blowing agent and polyol. Read the instructions and Material Safety Data Sheets carefully before use. Wear protective clothing (including long sleeves), gloves, goggles or safety glasses, and proper respiratory protection. Supplied air or an approved air-purifying respirator equipped with an organic vapor sorbent and a P100 particulate filter may be required to maintain exposure levels below ACGIH, OSHA, WEEL or other applicable limits. Provide adequate ventilation. Contents under pressure.

Building and/or construction practices unrelated to building materials could greatly affect moisture and the potential for mold formation. No material supplier including Dow can give assurance that mold will not develop in any specific system.

